

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A process for patinating articles comprising copper or a copper alloy by means of an ~~in-particular~~ aqueous patination solution containing copper ions, wherein the article is treated with the patination solution, ~~preferably by applying the patination solution to the article,~~ and the article which has been treated in this way is subjected to a maturing process, wherein during the maturing process, temperature and atmospheric humidity are controlled in a temperature- and humidity-controlled chamber, and wherein the maturing process encompasses the following maturing steps:

- allowing the treated article to rest at a first rest temperature and a first rest atmospheric humidity for a first rest time,
- irrigating the treated article at least once at an irrigation temperature and an irrigation atmospheric humidity for an irrigation time, and
- allowing the treated article to rest at a second rest temperature and a second rest atmospheric humidity for a second rest time.

2. – 3. (Cancelled)

4. (Currently Amended) The process as claimed in claim 1 [[3]], wherein the rest temperatures are in the range from 20°C to 70°C, ~~in particular from 25°C to 55°C~~, and the rest atmospheric humidities are in the range from 30% to 90%, ~~in particular from 40% to 50%~~.

5. (Currently Amended) The process as claimed in claim 1 [[3]] wherein the second rest temperature corresponds essentially to the first rest temperature and the second rest atmospheric humidity corresponds essentially to the first rest atmospheric humidity.

6. (Currently Amended) The process as claimed in claim 1 [[3]], wherein the irrigation temperature is in the range from 20°C to 70°C, ~~in particular from 25°C to 55°C~~, and the irrigation atmospheric humidity is in the range from 30% to 95%, ~~in particular from 65% to 80%~~.

7. (Currently Amended) The process as claimed in claim 1 [[3]], wherein the first rest time and the second rest time are each up to one week, ~~preferably from 2 to 3 days~~.

8. (Currently Amended) The process as claimed in claim 1 [[3]], wherein the irrigation time is up to one day, ~~preferably from 5 to 10 hours~~.

9. (Currently Amended) The process as claimed in claim 1, wherein the patination solution contains at least one copper salt, ~~preferably copper nitrate~~, in a proportion of from 1.5% to 20% by weight, ~~in particular in a proportion of from 3% by weight to 5% by weight~~.

10. (Currently Amended) The process as claimed in claim 1, wherein the patination solution contains at least one zinc salt, ~~preferably zinc chloride~~.

11. (Currently Amended) The process as claimed in claim 10, wherein the patination solution contains the zinc salt in a proportion of from 0.1% by weight to 5% by weight, ~~in particular in a proportion of from 0.2% by weight to 1% by weight~~.

12. (Currently Amended) The process as claimed in claim 1, wherein chloride and carbonate additives, ~~in particular sodium chloride, ammonium chloride, calcium chloride and/or ammonium carbonate~~, are present in the patination solution.

13. (Previously Presented) The process as claimed in claim 1, wherein at least one surface treatment selected from the group consisting of cleaning and roughening of the surface is carried out prior to the treatment of the article.

14. - 15. (Cancelled)

16. (Currently Amended) The process as claimed in claim 1, wherein a treatment temperature in the range from 30°C to 70°C, ~~in particular in the range from 40°C to 55°C~~, is selected in the treatment of the article with the patination solution.

17. (Currently Amended) The process as claimed in claim 1, wherein the patination solution is applied in at least two, ~~preferably 4—5~~, treatment steps.

18. (Previously Presented) The process as claimed in claim 1, wherein at least one surface after-treatment selected from the group consisting of sealing, lightening and darkening of the surface is carried out after the maturing process.

19. (Cancelled)

20. (Previously Presented) The process as claimed in claim 1, wherein the article to be patinated is selected from the group consisting of plate material, strip material, shaped part and ornament.

21. (Withdrawn) A patination solution for patinating articles comprising copper or a copper alloy in the form of a preferably aqueous copper salt solution, wherein the solution contains zinc ions.

22. (Withdrawn) The patination solution as claimed in claim 21, wherein it contains a zinc salt, in particular zinc chloride, preferably in a proportion of from 0.1% by weight to 5% by weight, in particular from 0.2% by weight to 1% by weight.

23. (Withdrawn) The patination solution as claimed in claim 21, wherein at least one copper salt, preferably copper nitrate, is present in a proportion of from 1.5% by weight to 20% by weight, in particular from 3% by weight to 5% by weight.

24. (Withdrawn) The patination solution as claimed in claim 21, wherein chloride and carbonate additives, in particular sodium chloride, ammonium chloride, calcium chloride and/or ammonium carbonate, are present in the solution.

25. (Withdrawn) A patinated article comprising copper or a copper alloy, which can be produced by a process as claimed in claim 1.

26. (Withdrawn) A patinated article comprising copper or a copper alloy, which has been produced by a process as claimed in claim 1.

27. (Withdrawn) The patinated article comprising copper or a copper alloy as claimed in claim 25 wherein it has the following structure:

- a base body comprising copper or a copper alloy selected from the group consisting of plate material, strip material, shaped part and ornament and

- at least one patina layer which is located on the base body and contains copper ions and zinc ions.

28. (Withdrawn) The patinated article as claimed in claim 25, wherein the thickness of the patina is from 0.02 to 0.06 mm, in particular from 0.03 to 0.05 mm.

29. (Withdrawn) The patinated article comprising copper or a copper alloy as claimed in claim 26 wherein it has the following structure:

- a base body comprising copper or a copper alloy selected from the group consisting of plate material, strip material, shaped part and ornament and
- at least one patina layer which is located on the base body and contains copper ions and zinc ions.

30. (Withdrawn) The patinated article as claimed in claim 26, wherein the thickness of the patina is from 0.02 to 0.06 mm, in particular from 0.03 to 0.05 mm.